

Gutzwiller wave function in the three-band Hubbard model: A variational Monte Carlo study

A. Oguri, T. Asahata, and S. Maekawa

Department of Applied Physics, Nagoya University, Nagoya 464-01, Japan

(February 1, 2008)

Abstract

The Gutzwiller wave function for the three-band Hubbard model on a two dimensional CuO_2 plane is studied by using the variational Monte Carlo (VMC) method in the limit $U_d \rightarrow \infty$, where U_d is the Coulomb repulsion between holes on a Cu site. The VMC results for the energy and the fraction of d -holes are compared with those of the Rice-Ueda type Gutzwiller approximation (GA). The difference between the VMC and the GA results are most pronounced at half-filling, and away from half-filling the two results agree well in both the hole-doped and the electron-doped cases. The doping dependence of the momentum distribution function is also studied.

PACS numbers: 74.20, 71.30.+h, 71.10.+x

I. INTRODUCTION

The Gutzwiller wave function (GF) has been used for microscopic investigation of strongly correlated electron systems such as the single-band Hubbard model,^{1–10} the periodic Anderson model,^{11–17} and the Kondo lattice model.^{18–20} In these last years, the three-band Hubbard model on a two dimensional CuO_2 plane²¹ have been studied extensively as a model for the high- T_c superconductors. The GF has been also applied to this model with the Rice-Ueda¹¹ type Gutzwiller approximation (GA),^{22–24} and with the variational Monte Carlo (VMC) method.^{25–27} Although the GF is a simple wave function, analytic evaluations of expectation values with the GF have been succeeded only in the single-band Hubbard model on a one dimensional chain.^{8,9} In the VMC method, the expectation values are calculated numerically taking the square of the wave function in the first-quantization formalism as a probability weight. The merit of the VMC method is that effects of the Gutzwiller projection operator which controls the number of doubly occupied sites and spatial correlations inherent in a starting Fermi sea can be taken into account exactly. These are treated with a mean-field like approximation in the GA. Using the VMC method, Yokoyama and Shiba⁶ have shown that the Brinkman-Rice (BR) transition² does not occur in the single-band Hubbard model. This result has been proved analytically in one dimensional case by Metzner and Vollhardt.⁸

In previous papers, we have studied the normal state properties in the GF for the three-band Hubbard model in the half-filled case,^{26,27} where the number of holes per unit cell is $n_h = 1.0$. We have confirmed that the BR transition, which occurs in the GA, is absent within the GF also in the three-band Hubbard model by using the VMC method. The purpose of this paper is to study effects of doping on the normal state properties. For this end, we calculate the energy and the fraction of d -holes away from half-filling both in the hole-doped ($n_h > 1.0$) and the electron-doped ($n_h < 1.0$) cases using a system which contains 6×6 Cu sites. For a comparison, we examine these quantities also by the GA. The results show that discrepancies of the VMC and the GA results are most pronounced

at half-filling, and away from half-filling the two results agree well when the doping rate $|\delta|$, which is defined by $n_h = 1.0 + \delta$, increases. Moreover, we study the momentum distribution function $n(k)$ using a 12×12 system. Outside the Fermi surface $n(k)$ is nonzero due to the strong Coulomb repulsion, and decreases when the wave number k approaches to the jump at the Fermi surface. This behavior seems to be one of the characteristics of the GF, and was seen also in the GF for the single-band Hubbard model.^{6,8}

In Sec. II, the GF for the three-band Hubbard model is introduced, and the outline of the VMC calculation is explained. The VMC results for the energy and the fraction of d -holes are compared with those of the GA for several doping rates in Sec. III. The momentum distribution function is studied in Sec. IV. A summary is given in Sec. V. In the appendix, details of the GA calculation are given, and its relation to the auxiliary-boson mean-field theory is discussed.

II. GUTZWILLER WAVE FUNCTION

The Hamiltonian of the three-band Hubbard model on a two dimensional CuO_2 plane is given, *in a hole notation*, by

$$\mathcal{H} = \mathcal{H}_{pd} + \Delta_0 (\widehat{N}_p - \widehat{N}_d) + U_d \sum_i n_{i\uparrow}^d n_{i\downarrow}^d, \quad (1)$$

$$\mathcal{H}_{pd} = t_{pd} \sum_{i,\sigma} \left[d_{i\sigma}^\dagger \left(p_{i+\hat{x}/2,\sigma} + p_{i+\hat{y}/2,\sigma} - p_{i-\hat{x}/2,\sigma} - p_{i-\hat{y}/2,\sigma} \right) + h.c. \right], \quad (2)$$

$$\widehat{N}_p = \sum_{i,\sigma} \left(p_{i+\hat{x}/2,\sigma}^\dagger p_{i+\hat{x}/2,\sigma} + p_{i+\hat{y}/2,\sigma}^\dagger p_{i+\hat{y}/2,\sigma} \right), \quad (3)$$

$$\widehat{N}_d = \sum_{i,\sigma} n_{i\sigma}^d, \quad (4)$$

where $d_{i\sigma}^\dagger$ creates a hole with spin σ in the Cu- $3d_{x^2-y^2}$ orbital at site i , $n_{i\sigma}^d = d_{i\sigma}^\dagger d_{i\sigma}$, $p_{i\pm\hat{x}/2,\sigma}^\dagger$ ($p_{i\pm\hat{y}/2,\sigma}^\dagger$) creates a hole in the O- p_x (O- p_y) orbital, and $\hat{x}$ ($\hat{y}$) is a vector in the x (y) direction whose length is equal to the distance between the nearest-neighboring Cu sites. The charge transfer energy Δ_0 is written in terms of the on-site energies for a hole on an O site ε_p and a Cu site ε_d as $\Delta_0 = (\varepsilon_p - \varepsilon_d)/2$ with $\varepsilon_p > \varepsilon_d$. For convenience, the zero

of energy has been chosen at $(\varepsilon_p + \varepsilon_d)/2 = 0$, and we will use the nearest neighboring p - d hopping matrix element t_{pd} as a unit of the energy, i.e., $t_{pd} = 1$. In this paper we concentrate on the case $U_d \rightarrow \infty$, where U_d is the Coulomb repulsion between holes on a Cu site. In this limit doubly occupied states are prohibited on Cu sites.

The Gutzwiller wave function for the three-band Hubbard model is given by^{22–26}

$$|\Psi(\tilde{\Delta})\rangle = P_d |\Phi(\tilde{\Delta})\rangle, \quad (5)$$

$$P_d = \prod_i \left[1 - n_{i\uparrow}^d n_{i\downarrow}^d \right], \quad (6)$$

where $\tilde{\Delta}$ is the variational parameter, and $|\Phi(\tilde{\Delta})\rangle$ is a ground state of a noninteracting Hamiltonian which contains $\tilde{\Delta}$ as a charge transfer energy

$$\tilde{\mathcal{K}} = \mathcal{H}_{pd} + \tilde{\Delta} (\widehat{N}_p - \widehat{N}_d). \quad (7)$$

The wave function $|\Psi(\tilde{\Delta})\rangle$ is an extension of the GF for the single-band Hubbard model¹ and the periodic Anderson model,^{11,17} and is constructed by projecting out the states with doubly occupied Cu sites from the starting Fermi sea (FS), i.e., $|\Phi(\tilde{\Delta})\rangle$. The optimal value of $\tilde{\Delta}$ is determined by minimizing the energy for given Hamiltonian parameter Δ_0 . If a Hartree-Fock approximation is applied to the Hamiltonian Eq. (1), the on-site energy on a Cu site is renormalized due to the Coulomb repulsion, and the charge transfer energy becomes smaller than the bare value Δ_0 . This Hartree-Fock picture gives a simple physical interpretation of the variational parameter $\tilde{\Delta}$. The one-particle eigenstates of $\tilde{\mathcal{K}}$ consist of the three bands: bonding-, antibonding-, and nonbonding-band. When the hole concentration is $0 \leq n_h \leq 2$, the bonding-band, which is the lowest band, is partially filled by holes, and the FS is written in the form

$$|\Phi(\tilde{\Delta})\rangle = \prod_{\substack{k \in \mathcal{F} \\ \sigma}} \gamma_{k\sigma}^\dagger |0\rangle, \quad (8)$$

$$\begin{aligned} \gamma_{k\sigma}^\dagger = & \sqrt{\frac{1}{2} \left(1 + \frac{\tilde{\Delta}}{\varepsilon_k} \right)} d_{k\sigma}^\dagger \\ & + i \sqrt{\frac{1}{2} \left(1 - \frac{\tilde{\Delta}}{\varepsilon_k} \right)} \left(\frac{V_{xk}}{V_k} p_{k\sigma}^{x\dagger} + \frac{V_{yk}}{V_k} p_{k\sigma}^{y\dagger} \right), \end{aligned} \quad (9)$$

where $V_{xk} = 2t_{pd} \sin(k_x/2)$, $V_{yk} = 2t_{pd} \sin(k_y/2)$, $V_k = \sqrt{V_{xk}^2 + V_{yk}^2}$, $\varepsilon_k = \sqrt{\tilde{\Delta}^2 + V_k^2}$, and $\mathcal{F}$ is a set of wave numbers in the FS. The operator $\gamma_{k\sigma}^\dagger$ creates a hole in the bonding-band, and $d_{k\sigma}^\dagger$, $p_{k\sigma}^{x\dagger}$, and $p_{k\sigma}^{y\dagger}$ are, respectively, the Fourier transforms

$$d_{k\sigma}^\dagger = \frac{1}{\sqrt{N_{\text{unit}}}} \sum_i d_{i\sigma}^\dagger e^{iqR_i}, \quad (10)$$

$$p_{k\sigma}^{x\dagger} = \frac{1}{\sqrt{N_{\text{unit}}}} \sum_i p_{i+\hat{x}/2,\sigma}^\dagger e^{iq(R_i+\hat{x}/2)}, \quad (11)$$

$$p_{k\sigma}^{y\dagger} = \frac{1}{\sqrt{N_{\text{unit}}}} \sum_i p_{i+\hat{y}/2,\sigma}^\dagger e^{iq(R_i+\hat{y}/2)}, \quad (12)$$

where N_{unit} is the number of the unit cells each of which contains the three sites CuO_2 . The summation with respect to i (R_i) runs over the Cu sites.

The energy expectation value, *per unit cell*, is written as

$$\begin{aligned} E(\tilde{\Delta}) &= \langle \mathcal{H} \rangle / N_{\text{unit}} \\ &= E_{pd}(\tilde{\Delta}) + \Delta_0 [n_p(\tilde{\Delta}) - n_d(\tilde{\Delta})], \end{aligned} \quad (13)$$

where $E_{pd}(\tilde{\Delta}) = \langle \mathcal{H}_{pd} \rangle / N_{\text{unit}}$, $n_p(\tilde{\Delta}) = \langle \hat{N}_p \rangle / N_{\text{unit}}$, $n_d(\tilde{\Delta}) = \langle \hat{N}_d \rangle / N_{\text{unit}}$, and

$$\langle \hat{\mathcal{O}} \rangle = \frac{\langle \Psi(\tilde{\Delta}) | \hat{\mathcal{O}} | \Psi(\tilde{\Delta}) \rangle}{\langle \Psi(\tilde{\Delta}) | \Psi(\tilde{\Delta}) \rangle}. \quad (14)$$

Since the total number of holes N_h is a conserved quantity, $n_p(\tilde{\Delta})$ is written in terms of $n_d(\tilde{\Delta})$: $n_p(\tilde{\Delta}) = n_h - n_d(\tilde{\Delta})$ with $n_h = N_h / N_{\text{unit}}$. Thus, the total energy for various Δ_0 can be obtained from the data of $E_{pd}(\tilde{\Delta})$ and $n_d(\tilde{\Delta})$. We calculate the expectation values, $\langle \hat{\mathcal{O}} \rangle$, numerically by using the Monte Carlo (MC) method taking the square of the Slater determinant as a probability weighting.^{5–7,17,28} In this method, the constraint of no doubly occupied Cu sites and spatial correlations inherent in $|\Phi(\tilde{\Delta})\rangle$ are treated exactly. Typically, 20 000–70 000 samples are used for the averages, and each sample is taken every 4–7 MC steps after 10 000 MC steps have been discarded for the relaxation, where one MC step means a set of N_h-3N_h trials for new configurations. When the acceptance ratio becomes small, that is the case for large $\tilde{\Delta}$, we increase the number of the samples and the sampling intervals for keeping the statistical independence of the samples. To estimate the statistical

fluctuation in the MC calculation, we divide the total samples into 10 groups and, if needed, show the maximum and the minimum among them as an error bar. We use a system with 6×6 unit cells (108 sites) for calculating $E_{pd}(\tilde{\Delta})$ and $n_d(\tilde{\Delta})$, and use a 12×12 system for the momentum distribution function. We choose the periodic boundary condition along the x -direction, and the antiperiodic boundary condition along the y -direction. With this boundary condition, $|\Phi(\tilde{\Delta})\rangle$ can be determined uniquely in the half-filled case.⁶

III. VMC AND GA RESULTS

In this section, we show the results for the doping dependence of the energy and the fraction of d -holes. The total number of holes used in the calculation is $N_h = 32, 36, 40, 48$, and 56, and the system size is $N_{\text{unit}} = 36$. Here the case of $n_h = 36/36$ corresponds to half-filling, and the other cases, $n_h < 1.0$, and, $n_h > 1.0$, correspond to the electron-doped and the hole-doped cases, respectively. We use $|t_{pd}|$ as units of energy.

In Figs. 1 and 2, the expectation values of the d -hole fraction $n_d(\tilde{\Delta})$ and the p - d hopping energy $E_{pd}(\tilde{\Delta})$ are shown as functions of the variational parameter $\tilde{\Delta}$. The solid circles ($\bullet$) denote the VMC results, and the solid lines denote the corresponding expectation values in the FS, i.e., $\langle \Phi(\tilde{\Delta}) | \hat{N}_d | \Phi(\tilde{\Delta}) \rangle / N_{\text{unit}}$ or $\langle \Phi(\tilde{\Delta}) | \mathcal{H}_{pd} | \Phi(\tilde{\Delta}) \rangle / N_{\text{unit}}$. Thus, the differences between the circles and the solid lines are due to effects of the projection operator P_d defined in Eq. (6). The statistical fluctuations due to the MC calculation are smaller than the size of the circles. Both of the results, $n_d(\tilde{\Delta})$ and $E_{pd}(\tilde{\Delta})$, show that the difference of the GF from the FS becomes large with increasing n_h . Because the doubly occupied states on Cu sites are projected out, the fraction of d -holes is smaller than that in the FS, and $n_d(\tilde{\Delta}) \leq 1.0$. For large $\tilde{\Delta}$, $n_d(\tilde{\Delta})$ tends to n_h in the electron-doped case (a), and tends to 1.0 in the half-filled (b) and the hole-doped cases (c)–(e). The projection operator P_d causes the loss of the hopping energy, so that $E_{pd}(\tilde{\Delta})$ is larger than that in the FS. For large $\tilde{\Delta}$, $E_{pd}(\tilde{\Delta})$ tends to zero in proportion to $1/\tilde{\Delta}$.²⁶ The hopping energy in the FS becomes minimum at $\tilde{\Delta} = 0.0$, which becomes deep when the hole concentration n_h increases. Correspondingly,

$E_{pd}(\tilde{\Delta})$ becomes minimum at small negative $\tilde{\Delta}$. In Fig. 3, the value of $\tilde{\Delta}$ which corresponds to the minimum of $E_{pd}(\tilde{\Delta})$ is plotted as a function of n_h . Since the restriction of the p - d hopping due to the projection P_d becomes *relatively* less important when the fraction of d -holes is decreased, the minimum of $E_{pd}(\tilde{\Delta})$ shifts to the negative value of $\tilde{\Delta}$. The shift becomes large with increasing n_h .

The expectation value of the total energy $E(\tilde{\Delta})$ is calculated substituting $E_{pd}(\tilde{\Delta})$, $n_d(\tilde{\Delta})$, and $n_p(\tilde{\Delta}) = n_h - n_d(\tilde{\Delta})$ into Eq. (13). In Fig. 4, $E(\tilde{\Delta})$ in the half-filled case is shown as a function of the variational parameter $\tilde{\Delta}$ for some given Δ_0 . When Δ_0 increases, the minimum of $E(\tilde{\Delta})$ becomes broad, and the value of $\tilde{\Delta}$ which corresponds to the minimum becomes large. This is due to the facts that the hopping energy $E_{pd}(\tilde{\Delta})$ has a minimum at $\tilde{\Delta} \simeq 0$, and the potential energy, which is the second term in Eq. (13) $\Delta_0 [n_p(\tilde{\Delta}) - n_d(\tilde{\Delta})]$, is a decreasing function of $\tilde{\Delta}$. The contribution of the potential energy to $E(\tilde{\Delta})$ in the half-filled case is larger than that in the doped cases, which can be seen from the value of $n_p(\tilde{\Delta}) - n_d(\tilde{\Delta})$ in the limit $\tilde{\Delta} \rightarrow \infty$

$$\lim_{\tilde{\Delta} \rightarrow \infty} [n_p(\tilde{\Delta}) - n_d(\tilde{\Delta})] = \begin{cases} -n_h & \text{for } n_h < 1.0 \\ n_h - 2 & \text{for } n_h \geq 1.0 \end{cases}.$$

Thus, although the qualitative feature of Fig. 4 is not changed by doping, the broadening of the energy minimum with increasing Δ_0 is most pronounced in the half-filled case. We have determined the minimum of $E(\tilde{\Delta})$ using a least-squares fit to a quadratic function around the stationary point. The energy can be determined with reasonable accuracy because an error for the energy is proportional to ϵ^2 , where ϵ is the error for the variational parameter $\tilde{\Delta}$ which corresponds to the energy minimum. The error ϵ becomes large when the minimum is broad. We will show the error bar due to finite ϵ if it is necessary. In Fig. 5, the optimal value of the variational parameter, $\tilde{\Delta}_{\text{opt}}$, is shown (a) as a function of Δ_0 , and (b) as a function of n_h . For small Δ_0 , $\tilde{\Delta}_{\text{opt}}$ is negative and a decreasing function of n_h because the total energy is mainly determined by the hopping energy $E_{pd}(\tilde{\Delta})$. For $\Delta_0 \gtrsim 2.0$, $\tilde{\Delta}_{\text{opt}}$ becomes maximum at $n_h = 1.0$ (b), and the peak becomes sharp with increasing Δ_0 . This is

because the total energy is dominated by the potential energy for large Δ_0 . When $\Delta_0 \gg 1.0$, the optimal value $\tilde{\Delta}_{\text{opt}}$ is proportional to Δ_0 .²⁶

In Figs. 6 and 7, the total energy and the d -hole fraction are shown as functions of Δ_0 , where the circles ($\bullet$) denote the VMC results, and the solid lines denote the GA results. Details of the GA calculation are given in the appendix. The difference between the VMC and the GA energy is large in the half-filled case (b), and becomes small away from half-filling both in the electron-doped case (a) and the hole-doped cases (c)-(e). Since the zero of energy has been chosen at $(\varepsilon_p + \varepsilon_d)/2 = 0$, the energy becomes maximum when the fractions of p -holes and the d -holes turn out to be the same, i.e., $n_d = n_p$ ($= n_h/2$). In Fig. 7, the error bars for n_d are mainly caused by finite ϵ . In the half-filled case (b), the BR transition occurs in the GA at $\Delta_0^c \approx 3.35$, and n_d becomes unity for $\Delta_0 \geq \Delta_0^c$. Although the BR transition does not occur within the GF,²⁶ the VMC results for n_d is close to unity for large Δ_0 , which means that holes tend to localize at Cu sites. Away from half-filling, the d -hole fractions with the VMC and the GA agree well. In Fig. 8, the VMC results are plotted as functions of n_h for several Δ_0 , where the lines are guide to the eye. For small Δ_0 , the energy decreases with increasing n_h . However, for $\Delta_0 \gtrsim 3.0$, the VMC energy becomes minimum at $n_h = 1.0$ and seems to show a cusp like behavior. If there is a jump in the slope, the system exhibits a phase transition to an insulating state with $n_d < 1.0$. The d -hole fraction, correspondingly, has a peak at $n_h = 1.0$ and becomes close to unity when Δ_0 is large, while n_d is an increasing function of n_h for $\Delta_0 \lesssim 1.0$. We note that beyond the GF the metal-insulator transition may occur in the three-band Hubbard model, which has been studied, for instance, by Dopf *et al* with the quantum Monte Carlo method.²⁹

IV. MOMENTUM DISTRIBUTION FUNCTION

The momentum distribution function for holes in the bonding-band is defined by

$$n(k) = \frac{1}{2} \sum_{\sigma} \langle \gamma_{k\sigma}^{\dagger} \gamma_{k\sigma} \rangle . \quad (15)$$

The operator $\gamma_{k\sigma}^\dagger$ defined in Eq. (9) is written in a linear combination of d and p -holes, and the coefficient for each orbit depends on the variational parameter $\tilde{\Delta}$. In this definition the momentum distribution function in the FS $|\Phi(\tilde{\Delta})\rangle$ is given by

$$\langle \Phi(\tilde{\Delta}) | \gamma_{k\sigma}^\dagger \gamma_{k\sigma} | \Phi(\tilde{\Delta}) \rangle = \begin{cases} 1.0 & \text{if } k \in \mathcal{F} \\ 0.0 & \text{if } k \notin \mathcal{F} \end{cases}.$$

The VMC calculation for $n(k)$ is performed in the real space using the expression which is obtained by substituting Eq. (9) and the Fourier transforms Eqs. (10)–(12) into Eq. (15). In Fig. 9, the momentum distribution function in the half-filled case (a), the hole-doped case with $n_h \simeq 1.0 + 0.833$ (b), and the electron-doped case with $n_h \simeq 1.0 - 0.833$ (c), are plotted for several $\tilde{\Delta}$ along the line shown in (d). Because of the antiperiodic boundary condition in the y -direction, the line is shifted from the usual symmetry directions in the Brillouin zone. In the Figure, the value of $\tilde{\Delta}$ is given. The corresponding Hamiltonian parameter Δ_0 is estimated from the data obtained in 6×6 systems, and is shown in the figure caption. The statistical fluctuations in $n(k)$ are smaller than the symbols in the figures. Inside the Fermi surface, $n(k)$ is almost flat, and the jump at the Fermi surface becomes small when $\tilde{\Delta}$ (or Δ_0) is large. The jump is finite when $1/\tilde{\Delta} \neq 0$. In the limit $\tilde{\Delta} \rightarrow \infty$, the jump vanishes in the half-filled and the hole-doped cases, while it remains finite in the electron-doped case. Nevertheless, in the hole-doped cases, the momentum distribution function for p -holes such as $\langle p_{k\sigma}^\dagger p_{k\sigma}^x \rangle$ has a jump which remains finite in the limit $\tilde{\Delta} \rightarrow \infty$. These tendencies can be confirmed analytically by expanding $\gamma_{k\sigma}^\dagger$ and $|\Psi(\tilde{\Delta})\rangle$ with respect to $1/\tilde{\Delta}$, as it was performed in Ref. 26. Outside the Fermi surface, $n(k)$ becomes nonzero due to the Coulomb repulsion. The holes excited to the outside are d -holes because the projection operator P_d acts only for d -holes and commutes with the operators for p -holes. The value of $n(k)$ outside the Fermi surface decreases when k approaches to the jump. This behavior seems to be one of the characteristics of the Gutzwiller wave function, and was seen also in the GF for the single-band Hubbard model.^{6,8}

V. SUMMARY

In summary, we have studied the normal-state properties of the three-band Hubbard model based on a Gutzwiller wave function, and have compared the VMC results with those of the GA. The results for the energy and the fraction of d -holes show that the discrepancies of the VMC and the GA are most pronounced at half-filling. Away from half-filling the results with the two methods agree well both in the hole-doped and the electron-doped cases. The momentum distribution function for the holes in the bonding-band, $n(k)$, is almost flat inside the Fermi surface. Outside the Fermi surface $n(k)$ is finite and decreases when k approaches to the jump at the Fermi surface as that in the GF for the single-band Hubbard model.

ACKNOWLEDGMENTS

This work was supported by a Grant-in-Aid for Scientific Research on Priority Areas from the Ministry of Education, Science, and Culture of Japan.

APPENDIX A: GUTZWILLER APPROXIMATION

In this appendix, we demonstrate the calculation of the Rice-Ueda type Gutzwiller approximation (GA).¹¹ This approximation was applied to the three-band Hubbard model by several authors. Miyake *et al*²² and Sarker²⁴ studied the model with finite U_d , and Mayou *et al*²³ studied the case in which both U_d and U_p are ∞ . Here U_p is the Coulomb repulsion between holes on an O site. These authors, however, did not investigate the Brinkman-Rice transition, which has been studied with the auxiliary-boson method by other authors.^{30–32} The relation between the GA and the auxiliary-boson method is briefly reviewed here.

1. Method

The Gutzwiller wave function in the limit $U_d \rightarrow \infty$ Eq. (6) is generalized for the model with finite U_d by introducing an additional variational parameter g as

$$|\Psi(g, \tilde{\Delta})\rangle = \prod_i \left[1 - (1 - g) n_{i\uparrow}^d n_{i\downarrow}^d \right] |\Phi(\tilde{\Delta})\rangle. \quad (\text{A1})$$

In the GA, the expectation value for the p - d hopping energy, $\langle \Psi | \mathcal{H}_{pd} | \Psi \rangle / \langle \Psi | \Psi \rangle$, is replaced by that for a noninteracting band with renormalized parameters $\langle \Phi_{\text{eff}} | \sqrt{q} \mathcal{H}_{pd} | \Phi_{\text{eff}} \rangle$. Then the energy expectation value is given by^{22,24}

$$\begin{aligned} E_{\text{GA}} &= \langle \Phi_{\text{eff}} | \mathcal{K}_{\text{eff}} | \Phi_{\text{eff}} \rangle + U_d d_{\text{Cu}} N_{\text{unit}} \\ &+ (\Delta_0 - \Delta_{\text{eff}}) \langle \Phi_{\text{eff}} | (\widehat{N}_p - \widehat{N}_d) | \Phi_{\text{eff}} \rangle, \end{aligned} \quad (\text{A2})$$

where d_{Cu} is the fraction of the doubly occupied Cu sites, and $|\Phi_{\text{eff}}\rangle$ is a ground state of an effective Hamiltonian

$$\mathcal{K}_{\text{eff}} = \sqrt{q} \mathcal{H}_{pd} + \Delta_{\text{eff}} (\widehat{N}_p - \widehat{N}_d), \quad (\text{A3})$$

with

$$q = \frac{(n_d/2 - d_{\text{Cu}})}{(n_d/2)(1 - n_d/2)} \left[\sqrt{1 - n_d + d_{\text{Cu}}} + \sqrt{d_{\text{Cu}}} \right]^2. \quad (\text{A4})$$

In deriving Eq. (A2), a configurational dependence in the starting Fermi sea $|\Phi(\tilde{\Delta})\rangle$ defined in Eq. (8) is neglected, and a dominant-term approximation is used for d_{Cu} and n_d .^{11,16} The condition for the dominant-term with respect to d_{Cu} is given by

$$g^2 = \frac{d_{\text{Cu}}(1 - n_d - d_{\text{Cu}})}{(n_d/2 - d_{\text{Cu}})^2}. \quad (\text{A5})$$

Thus the original parameter g is written as a function of n_d and d_{Cu} . Since the condition for the dominant-term with respect to n_d can not be written in a simple analytic form,¹⁶ the other original parameter $\tilde{\Delta}$ cannot be determined within the GA. The parameter Δ_{eff} in Eqs. (A2) and (A3) is introduced in order to treat this condition approximately, and is different

from the original parameter $\tilde{\Delta}$. The value of Δ_{eff} and d_{Cu} are determined by minimizing the energy functional E_{GA} for given Δ_0 and U_d .

The effective Hamiltonian $\mathcal{K}_{\text{eff}}$ can be easily diagonalized, and the one-particle eigenstates depend only on the ratio of Δ_{eff} to the renormalized value of the transfer integral $\sqrt{q}|t_{pd}|$

$$\alpha = \Delta_{\text{eff}}/\sqrt{q}|t_{pd}|. \quad (\text{A6})$$

For $0 \leq n_h \leq 2$, the d -hole fraction, $n_d = \langle \Phi_{\text{eff}} | \hat{N}_d | \Phi_{\text{eff}} \rangle / N_{\text{unit}}$, and the ground state energy of the effective Hamiltonian, $\kappa_{\text{eff}} = \langle \Phi_{\text{eff}} | \mathcal{K}_{\text{eff}} | \Phi_{\text{eff}} \rangle / N_{\text{unit}}$, are given by

$$\begin{aligned} n_d &= \frac{1}{N_{\text{unit}}} \sum_{k \in \mathcal{F}} \left(1 + \frac{\Delta_{\text{eff}}}{\sqrt{\Delta_{\text{eff}}^2 + q V_k^2}} \right) \\ &= \frac{1}{2} n_h + \int_{-1}^{\nu_c} d\nu \, \rho(\nu) \frac{\alpha}{\sqrt{\alpha^2 + 4(1 - \nu)}}, \end{aligned} \quad (\text{A7})$$

and

$$\begin{aligned} \kappa_{\text{eff}} &= -\frac{2}{N_{\text{unit}}} \sum_{k \in \mathcal{F}} \sqrt{\Delta_{\text{eff}}^2 + q V_k^2} \\ &= -2\sqrt{q}|t_{pd}| \int_{-1}^{\nu_c} d\nu \, \rho(\nu) \sqrt{\alpha^2 + 4(1 - \nu)}, \end{aligned} \quad (\text{A8})$$

where $\rho(\nu) = \sum_k \delta(\nu - \nu_k) / N_{\text{unit}}$, with $\nu_k = (\cos k_x + \cos k_y)/2$. The parameter ν_c is determined by the hole concentration n_h as

$$n_h = 2 \int_{-1}^{\nu_c} d\nu \, \rho(\nu), \quad (\text{A9})$$

and $\rho(\nu)$ is written using the complete elliptic integral of the first kind $K(x)$ as $\rho(\nu) = 2K(\sqrt{1 - \nu^2})/\pi^2$. Substituting Eq. (A7) into Eq. (A4), the factor q is written as a function of α and d_{Cu} . Then other quantities Δ_{eff} , κ_{eff} and E_{GA} are also written as functions of α and d_{Cu} using Eqs. (A6), (A8), and Eq. (A2) with $q = q(\alpha, d_{\text{Cu}})$. When $0 \leq n_h \leq 2$, the conditions for the energy minimum, $\partial E_{\text{GA}}/\partial \alpha = 0$ and $\partial E_{\text{GA}}/\partial d_{\text{Cu}} = 0$, are obtained as

$$\Delta_0 = \Delta_{\text{eff}} - \frac{1}{2} \frac{\partial q}{\partial n_d} T, \quad (\text{A10})$$

$$U_d = \frac{\partial q}{\partial d_{\text{Cu}}} T, \quad (\text{A11})$$

with

$$T = \int_{-1}^{\nu_c} d\nu \, \rho(\nu) \frac{4(1-\nu)t_{pd}^2}{\sqrt{\Delta_{\text{eff}}^2 + 4q(1-\nu)t_{pd}^2}}. \quad (\text{A12})$$

2. Results for $U_d \rightarrow \infty$

In the limit $U_d \rightarrow \infty$, the doubly occupied states are prohibited on Cu sites, and the factor q is written substituting $d_{\text{Cu}} \equiv 0$ in to Eq. (A4) as

$$q = \frac{1 - n_d}{1 - n_d/2}. \quad (\text{A13})$$

The optimal value of the ratio α is determined by solving Eq. (A10). We have calculated the integrals in Eqs. (A7)–(A9) numerically, and obtained the GA results for energy and the d -hole fraction shown in Figs. 6 and 7. In Fig. 10, results for q and Δ_{eff} are shown as functions of Δ_0 for several n_h . At half-filling, the Brinkman-Rice transition occurs at $\Delta_0 = \Delta_0^c$ (≈ 3.35 in units of $|t_{pd}|$). The analytic expression for Δ_0^c can be obtained by expanding E_{GA} with respect to $1/\alpha$ as

$$\Delta_0^c = 2\sqrt{2}\sqrt{1 + (2/\pi)^2} |t_{pd}|. \quad (\text{A14})$$

For $\Delta_0 \geq \Delta_0^c$, Δ_{eff} is a two-valued function of Δ_0 when $n_h = 1.0$. The value of Δ_{eff} for $n_h = 1 \pm 0$, $\Delta_{\text{eff}}^{\pm 0}$, can be obtained by substituting $n_d = 1.0$ and $\nu_c = 0.0$ into Eq. (A10) as

$$\Delta_{\text{eff}}^{\pm 0} = \left(\Delta_0^c \mp \sqrt{\Delta_0^2 - \Delta_0^{c2}} \right) / 2. \quad (\text{A15})$$

For $n_h > 1.0$, Δ_{eff} tends to zero in the limit $\Delta_0/|t_{pd}| \rightarrow \infty$. This is because the renormalization factor q tends to zero while the ratio α defined in Eq. (A6) has to be smaller than a finite value which is determined by Eq. (A7) with the condition $n_d = 1.0$. On the other hand, in the electron-doped cases there is no upper bound in α , and $q > 0.0$. Thus, Δ_{eff} increases with Δ_0 for $n_h < 1.0$. The charge excitation gap ϵ_{gap} , defined by a discontinuity of the chemical potential, can be also obtained analytically as

$$\epsilon_{\text{gap}} = \left. \frac{dE_{\text{GA}}^{(o)}}{dN_h} \right|_{n_h=1+0} - \left. \frac{dE_{\text{GA}}^{(o)}}{dN_h} \right|_{n_h=1-0}, \quad (\text{A16})$$

$$= \begin{cases} 0 & \text{for } \Delta_0 < \Delta_0^c \\ 2\sqrt{\Delta_0^2 - \Delta_0^{c2}} & \text{for } \Delta_0 \geq \Delta_0^c \end{cases},$$

where $E_{\text{GA}}^{(o)}$ is the minimized value of E_{GA} . For $\Delta_0 \geq \Delta_0^c$, ϵ_{gap} is finite and equal to twice of the jump in Δ_{eff} , i.e., $\epsilon_{\text{gap}} = 2(\Delta_{\text{eff}}^{-0} - \Delta_{\text{eff}}^{+0})$.

3. Remarks

The basic equations presented in this appendix, Eqs. (A2)–(A4), seems to be equivalent to those obtained by Balseiro *et al*³¹ applying a functional integral approach due to Kotliar and Ruckenstein³³ to the three-band Hubbard model. They have, however, neglected the ν dependence of $\rho(\nu)$, so that their results in the limit $U_d \rightarrow \infty$ differ from ours quantitatively. The energy functional obtained by Grilli *et al* within an auxiliary-boson mean-field theory³⁰ is also similar to that in the GA. The renormalization factor in their theory, however, is different from Eq. (A13), and is equal to the number of the auxiliary-bosons, i.e., $q \Rightarrow 1 - n_d$. Thus, the critical value Δ_0^c obtained in auxiliary-boson mean-field theory is a factor $\sqrt{2}$ smaller than Eq. (A14), which comes from the denominator of Eq. (A13) in the limit $n_d \rightarrow 1$. Similar results have also been obtained by Hirashima *et al* with the exact treatment of the local constraint of no doubly occupied Cu sites within the leading order of the $1/N$ -expansion,³² in which, specifically, the critical value Δ_0^c is the same as that of the auxiliary-boson mean-field theory.

REFERENCES

- ¹ M. C. Gutzwiller , Phys. Rev. Lett **10**, 159 (1963); Phys. Rev. **134**, A923 (1964); **137**, A1726 (1965).
- ² W. F. Brinkman and T. M. Rice, Phys. Rev. B **2**, 4302 (1970).
- ³ T. Ogawa, K. Kanda and T. Matsubara, Prog. Theor. Phys. **53**, 614 (1975).
- ⁴ D. Vollhardt, Rev. Mod. Phys. **56**, 99 (1985).
- ⁵ P. Horsch and T. A. Kaplan, J. Phys. C **16**, L1203 (1983).
- ⁶ H. Yokoyama and H. Shiba, J. Phys. Soc. Jpn. **56**, 1490 (1987); **59**, 3669 (1990)
- ⁷ C. Gros, R. Joint, and T. M. Rice, Phys. Rev. B **36**, 381 (1987).
- ⁸ W. Metzner and D. Vollhardt, Phys. Rev. Lett. **59**, 121 (1987); Phys. Rev. B **37**, 7382 (1988).
- ⁹ F. Gebhard and D. Vollhardt, Phys. Rev. Lett. **59**, 1472 (1987); Phys. Rev. B **38**, 6911 (1988).
- ¹⁰ P. G. J. van Dongen, F. Gebhard, and D. Vollhart, Z. Phys. B **76**, 199 (1989)
- ¹¹ T. M. Rice and K. Ueda, Phys. Rev. B **34**, 6420 (1986); Phys. Rev. Lett **55**, 995 (1985); **55**, 2093(E) (1985).
- ¹² C. M. Varama, W. Weber and L. J. Randall, Phys. Rev. B **33**, 1015 (1986).
- ¹³ B. H. Brandow, Phys. Rev. B **33**, 215 (1986).
- ¹⁴ P. Fazekas and B. H. Brandow, Phys. Scr. **36**, 809 (1987).
- ¹⁵ A. Oguchi, Prog. Theor. Phys. **77**, 278 (1987).
- ¹⁶ V. Ž. Vulović and E. Abrahams, Phys. Rev. B **36**, 2614 (1987).
- ¹⁷ H. Shiba, J. Phys. Soc. Jpn. **55**, 2765 (1986).

- ¹⁸ P. Fazekas and H. Shiba, *Int. J. Modern. Phys. B* **5**, 289 (1991).
- ¹⁹ P. Fazekas and E. Müller-Hartmann, *Z. Phys. B* **85**, 285 (1991).
- ²⁰ H. Shiba and P. Fazekas, *Prog. Theor. Phys. Suppl.* **101**, 403 (1990).
- ²¹ V. J. Emery, *Phys. Rev. Lett.* **58**, 2794 (1987).
- ²² K. Miyake, T. Matsuura, K. Sano, and Y. Nagaoka, *J. Phys. Soc. Jpn.* **57**, 722 (1988).
- ²³ D. Mayou, D. Nguyen Manh, and J. P. Julien, *Solid State Commun.* **68**, 665 (1988).
- ²⁴ S. K. Sarker, *Phys. Rev. B* **39**, 2155 (1989).
- ²⁵ S. N. Coppersmith, *Phys. Rev. B* **41**, 8711 (1990); **42**, 2259 (1990).
- ²⁶ A. Oguri and T. Asahata, *Phys. Rev. B* **46**, 14073 (1992)
- ²⁷ A. Oguri, T. Asahata, and S. Maekawa, *Physica B*, in press.
- ²⁸ D. Ceperley, G. V. Chester, and M. Kalos, *Phys. Rev. B* **16**, 3081 (1977).
- ²⁹ G. Dopf, A. Muramatsu, T. Kraft and W. Hanke, *Physica B* **165 & 166**, 1015 (1990);
G. Dopf, A. Muramatsu, and W. Hanke, *Phys. Rev. Lett.* **68**, 353 (1992).
- ³⁰ M. Grilli, B. G. Kotliar, and A. J. Millis, *Phys. Rev. B* **42**, 329 (1990).
- ³¹ C. A. Balseiro, M. Avignon, A. G. Rojo, and B. Alascio, *Phys. Rev. Lett.* **62**, 2624 (1989).
- ³² D. S. Hirashima, Y. Ōno, K. Miura, T. Matsuura, and H. Jichu, *J. Phys. Soc. Jpn.* **60**,
2269 (1991); H. Jichu, T. Matsuura, and Y. Kuroda, *J. Phys. Soc. Jpn.* **59**, 2820 (1990).
- ³³ G. Kotliar and A. E. Ruckenstein, *Phys. Rev. Lett.* **57**, 1362 (1986).

FIGURES

FIG. 1. The expectation value of the fraction of d holes $n_d(\tilde{\Delta})$ as a function of variational parameter $\tilde{\Delta}$ (in units of $|t_{pd}|$) for several values of the hole concentration n_h . The circles ($\bullet$) denote the VMC results in the Gutzwiller wave function $|\Psi(\tilde{\Delta})\rangle$, and the solid lines denote the d -hole fraction in the Fermi sea $|\Phi(\tilde{\Delta})\rangle$.

FIG. 2. The expectation value of the p - d hopping energy, *per unit cell*, $E_{pd}(\tilde{\Delta})$ (in units of $|t_{pd}|$) for several n_h . The circles ($\bullet$) denotes the VMC results in the GF, and the lines denote the corresponding expectation values in the FS.

FIG. 3. The value of $\tilde{\Delta}$ which corresponds to the minimum of $E_{pd}(\tilde{\Delta})$ (in units of $|t_{pd}|$).

FIG. 4. The expectation value of the total energy, *per unit cell*, $E(\tilde{\Delta})$ in the half-filled case for $\Delta_0 = 0.5, 1.0$, and 1.5 (in units of $|t_{pd}|$) with $\Delta_0 = (\varepsilon_p - \varepsilon_d)/2$. The origin of energy is taken to be $(\varepsilon_p + \varepsilon_d)/2 = 0$.

FIG. 5. The optimal value of the variational parameter $\tilde{\Delta}_{\text{opt}}$ (in units of $|t_{pd}|$) as a function of (a) Δ_0 , and (b) n_h . The lines in (b) are just guide to the eye.

FIG. 6. Variational results for the total energy, *per unit cell*, as a function of Δ_0 for several n_h (in units of $|t_{pd}|$). The circles ($\bullet$) denote the VMC results, and the solid lines denote the GA results.

FIG. 7. Variational results for the fraction of d -holes n_d as a function of Δ_0 (in units of $|t_{pd}|$). The circles ($\bullet$) denote the VMC results, and the solid lines denote the GA results.

FIG. 8. Doping dependence of the VMC results: (a) the total energy *per unit cell* and (b) the d -hole fraction, for several values of Δ_0 . The lines are just guide to the eye.

FIG. 9. The momentum distribution function for holes in the bonding-band $n(k)$ defined in Eq. (15): (a) the half-filled case ($n_h = 144/144$) with $\tilde{\Delta} = 0.1, 1.0, 10.0$, and 25.0 (in units of $|t_{pd}|$) which correspond to the optimal value for $\Delta_0 = 0.3, 1.0, 2.8$, and 4.0 , respectively, (b) the hole-doped case ($n_h = 156/144$) with $\tilde{\Delta} = 0.1, 1.0$, and 10.0 which correspond to the optimal value for $\Delta_0 = 0.4, 1.1$, and 4.0 , respectively, (c) the electron-doped case ($n_h = 132/144$) with $\tilde{\Delta} = 0.1, 1.0$, and 10.0 which correspond to the optimal value for $\Delta_0 = 0.2, 0.9$, and 3.7 , respectively, (d) k -points for a 12×12 system with the periodic-antiperiodic boundary condition, where the solid and open circles denote, respectively, the occupied and unoccupied states in $|\Phi(\tilde{\Delta})\rangle$ for $n_h = 1.0$.

FIG. 10. The GA results for (a) q , and (b) Δ_{eff} as functions of Δ_0 (in units of $|t_{pd}|$) for several n_h .